CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548
Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID : CP-2020-01-10-31 **Date: 11-11-19**

Project Name : Improvements to Roads and Drains at Yelahanka Old Town areas Gandhinagara SC/ST Areas and surrounding areas in Ward No. 01 Yelahanka Sub division.

Agency : M/s. Technical Manager (West), KRIDL, Bangaluru, 5th Block, 17th Main Shivakumar Swamy Building, Bhashyam Circle Bangalore: 560010

Customer's Reference : BBMP/EE/YNK.D/W.O/000160/2019-20

Date of Receipt : 08-11-19

Sample Type : Birla Super 53grade

Reference to BIS codes : IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification ,
IS 4031 (Part 1,2 3,4,5, 6,11):1988
IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4
IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5
IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6
IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5
IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5
IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6

Date of test : 09-11-19

Environmental Conditions during test : Temperature: 26°C
Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	2.46	–
2	Finess by Air permeablity method (m^2/kg,Min)	255.8	225m^2/kg, Min
3	Density (gm/cc)	3.12	–
4	Standard Consistency (%)	28.5%	Not specified
5	Initial Setting time	175 minutes	Not less than 30 minutes
6	Final Setting time	280 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1mm	Not more than 10 mm

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2020-01-10-31** **Date: 11-11-19**

Project Name : Improvements to Roads and Drains at Yelahanka Old Town areas Gandhinagara SC/ST Areas and surrounding areas in Ward No. 01 Yelahanka Sub division.

Agency : M/s. Technical Manager (West), KRIDL, Bangaluru, 5th Block, 17th Main Shivakumar Swamy Building, Bhashyam Circle Bangalore: 560010

Customer's Reference : BBMP/EE/YNK.D/W.O/000160/2019-20

Date of Receipt : 08-11-19

Sample Type : 40mm down size coarse aggregate

Reference to BIS codes : IS: 383:2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1,3,4) RA2011
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
IS 2386 Part 4: Mechanical Properties

Date of test : 08-11-19

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : **15000** **grams**

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	234	234	1.6	98.4	90-100
3	20 mm	5334	5568	37.1	62.9	30-70
4	10 mm	4788	10356	69.0	31.0	10-35
5	4.75 mm	4354	14710	98.1	1.9	0-5
6	Pan	290	15000	100.0	0	---

AE

AE-1

CIVIL PRO Sig..... Date..... BANGALORE

Scanned by CamScanner